



MAZZONETTO Spa
Via A. Ceccon, 10 - 35010 Loreggia (PD)
t. +39 049 9322611 - f. +39 049 9322650
mazzonetto@mazzonettometalli.it
www.mazzonettometalli.it



COPPER BARS Cu-ETP

Standard	
UNI EN 12167; UNI EN 1652; UNI EN 12167/99	
Technical features:	
Material designation symbol:	Cu-ETP
Density	8.93 kg/dm ³
Melting temperature	1083° C
Tensile strength	230 MPa min.
Elongation	12% min.
Brinell hardness	65-90 HB
Chemical composition:	
Copper (Cu)	99.90%
Oxygen (O)	0.04% max.
Dimensional characteristics:	
Standard thicknesses	2 – 3 – 4 – 5 mm
Bars length	4000 – 4200 mm
Standard widths	20 – 25 – 30 mm
Use:	
Civil and industrial building industry	